




IS FAILURE FORENSICS MORE IMPORTANT THAN DAMAGE TOLERANCE IN ASSESSING DEFECTS IN DISBONDING STRUCTURES?

Dr. Maxwell Davis PSM,
B.Eng (Mech.), M. Eng (Mech.), PhD, RPEQ

Director, Adhesion Associates Pty. Ltd.
www.adhesionassociates.com

Introduction

- Damage Tolerance Analysis (DTA) is effective for managing cracks in metallic aircraft structures
 - Demonstrate strength, fatigue resistance with defects of a known size
 - Mandated by FAR 2x.573
- DTA often used for bonded structures and joints
 - Testing, analysis assume localised bond separation in good bond



- Some types of defects change bond strength and negate the applicability of DTA
- This presentation demonstrates that adhesive bond failure forensics is essential to management of bond structural integrity




Adhesive bond failure types

- Three types of bond failure:
 - Cohesion failure
 - Adhesive layer is fractured
 - High strength
 - Adhesion failure
 - Separates from the surface of the adherend(s)
 - Low (no?) strength
 - Mixed-mode failure
 - Variable combination of adhesion and cohesion failure
 - Intermediate strength
- The features of these failure types and the implications to DTA will be discussed




COHESION FAILURE



ADHESION FAILURE



MIXED-MODE FAILURE




Adhesive bonding mechanisms

- Adhesive bonds rely on chemical bonds at the interface
 - Easy to generate short-term strength with simple treatments
- Long-term strength depends on the durability of those interfacial chemical bonds
- Interfacial degradation over time may cause adhesion, mixed-mode failure → lower strength
 - Due to hydration of surface oxides over time (metals) e.g.
 $\text{Al}_2\text{O}_3 \rightarrow \text{Al}_2\text{O}_3 \cdot 2\text{H}_2\text{O}$
 - Chemical metal-to-adhesive bonds dissociate, causing disbonding
- Failure may happen without **any** flight loads



Application of DTA to adhesives

- DTA of adhesive bonds is usually based on:
 - Strength tests with embedded artificial disbonds, or
 - FEA with artificial defects in model
- Both methods:
 - Infer surrounding adhesive maintains original strength
 - Assume a defect combined with loads cause failure




- DTA is only applicable for localised defects occurring in otherwise pristine bonds



Defining the issue

- Why is bond failure forensics important?
- Because FARs and DTA assume cohesion failure
- Real failures often involve adhesion or mixed-mode failure at lower strength
- Assumptions for DTA about residual bond strength are **invalid** for most defect types
- Type of defect must be correctly identified to verify applicability of DTA



Limitations of NDI for adhesive bonds

- DTA of adhesive bonds requires effective NDI
- NDI depends directly on detecting air gaps
- NDI can not assess the integrity of the adhesive-to-adherend interface
 - No air gaps
- NDI can not assess bond strength
 - Double-sided adhesive tape will pass the “tap” test
- Can only find an in-service defect after disbonding has commenced





Limitations of DTA

- Adhesive problems which are not compatible with DTA:
 - Interfacial degradation in service
 - Mixed-mode or adhesion failure
 - Micro-voiding during production leading to fatigue failure, and
 - Ineffective (injection) repair of production and service disbonds
- These problems:
 - May not be detectable using post-production NDI
 - May result in significant reduction of bond strength
 - May not be localised to just the detectable defects



Cohesion failure

- Occurs through carrier cloth
- Strength is high
- NDI can find large defects
- DTA is appropriate




- Design causes:
 - Thermal stresses
 - Stiffness mismatch
 - Inadequate bond overlap
 - Inadequate temp. capability
 - Addressed by certification
- Production causes:
 - Macro and micro voids
- Service causes:
 - Overload




Cohesion failure due to macro-voids

- Large voids in bondline
- Found by post-production NDI
- Residual bond overlap may be inadequate
- Surrounding adhesive is strong
- DTA *is* appropriate
- Often “repaired” by injection
 - Discussed later
- **NOT** caused by service loads or environment
- This is what is modelled by DTA




Cohesion failure due to micro-voids

- Widespread multiple small voids
- Evolution of absorbed moisture during production cure cycle
- Sufficient contact to pass NDI
- Total defect size may exceed DTA
 - Bond is weak
- Micro-voids do not initiate in service
 - May cause disbonds from fatigue, impact, high loads in service



Bonded
Joint



Sandwich
Panel




Significance of micro-voiding

- **FM300 adhesive exposed to 30°C and 70% RH for 4 hrs**
 - 53% loss of T-peel strength (ASTM 1876)
 - 28% loss of honeycomb peel strength (ASTM D1781)
- Suppose bonds are certified in dry environment but production is outsourced to Gybrobia (30°C, 70% RH), exposure > 4hrs
- Honeycomb peel: $\text{Strength} = 1.5 \times \text{DLL} \times 0.72$
 $= 1.08 \times \text{DLL}$
- T-peel: $\text{Strength} = 1.5 \times \text{DLL} \times 0.47$
 $= 0.705 \times \text{DLL}$
- Strength is marginal at DLL for honeycomb peel, unconservative for T-peel
- Micro-voids also reduce shear strength
- DTA inappropriate unless based on reduced strength



Adhesion failure

- Fully hydrated bond
 - Very weak
 - Fails at interface
- Causes
 - Poor processing (contamination)
 - Interfacial degradation in service





- NDI can only find disbonds *after they occur*
- DTA inappropriate
 - Strength is much lower than certification tests



Mixed-mode failure

- Partially hydrated bond
 - Some adhesion/cohesion failure
 - Fails away from carrier cloth
- Failure occurred before interface fully degraded
 - Reduced strength




- Failure may occur without pre-existing disbond
 - Not detected by NDI
 - DTA inappropriate
- Structure **IS** certainly weaker




Explaining mixed-mode failures

- Cohesion failure occurs through carrier cloth
- As interface degrades:
 - Mixed-mode failure occurs towards interface
 - Strength reduces
- Eventually adhesion failure occurs at interface
 - Very weak
- Safety investigators note:
 - Thin residue of adhesive on surfaces do **NOT** mean strong cohesion failure



Let's be clear

- NDI only finds disbonds after complete separation
- Regulations, damage tolerance assume cohesion failure
- NDI can't find mixed-mode degradation until adhesion defect actually occurs
- *Bond may fail mixed-mode at low loads before any disbond can be detected*
- DTA ineffective for mixed-mode, adhesion failures, microvoids



- There is a real risk to continuing airworthiness by applying DTA to these defects



In-service defects

- Defects discovered in service must be:
 - Mixed-mode failure
 - Adhesion failure or
 - Fatigue failure due to micro-voiding
- Fatigue can only occur in conjunction with pre-existing defects or bad designs
- Only detected by NDI *after* disbonding has initiated
- For short overlap lengths, failure may occur without detectable defects
- NOT represented by DTA based on high bond strength
 - Strength of surrounding adhesive is *a/ways* reduced




Case study: helicopter crash

- Aircraft tracking to pick up tourists in tropical location
- Experienced pilot only occupant
 - >5000 hrs, >3000 on type
- Clear sunny day, light winds, approx 500 ft ASL
- One blade departs plane of rotation, multiple strikes on fin and boom, aircraft crashed into sea, pilot deceased
- Blade had been inspected 80hrs before crash
 - Defect found within SRM limits - (tap test)
 - Not located at subsequent bond failure sites
- Investigator eliminated other causes except for failure of main rotor blade



Case study: helicopter crash

- Adhesion, mixed-mode failure over large proportion of blade
- Would be substantially weaker than original manufacture
- Very short overlap length




Case study: helicopter crash

- Can not definitively state bond failure caused the crash
 - Causal and consequential mixed-mode failures are similar
- Equally not possible to exclude weak bond strength as a significant factor
- Parts of blade first items in debris path
- Investigator concluded that in the absence of other causes, blade failure due to bond degradation was the most probable cause of the crash
- Official report is yet to be released



Preventing hydration

- Adhesion and mixed-mode failures are avoided by hydration resistant interfacial chemical bonds
 - Depends totally on the method used to prepare the surface for bonding
- Most effective means to demonstrate: wedge test ASTM D3762



- Acceptance criteria in DOT/FAA/AR – TN06/57 *Best Practice in Adhesive Bonded Structures and Repairs*
- Bonds meeting these requirements have a demonstrated history
 - RAAF twenty years < 0.07% bond failures (technician malfunctions)
 - USAF fourteen years no failures reported
- Some OEM processes will not meet these requirements
- **Many** SRM repair methods are also deficient



Regulations, policy and advice

- FAR 2x.573 analysis or testing with artificial disbonds, NDI and/or proof testing
 - Won't prevent adhesion or mixed-mode failure in later service
- FAR 2x.603 processes must produce a “sound” structure
- AC20-107-B recently recognised adhesion failures
 - No certification if adhesion failure occurs
 - In-service adhesion failures, part should be quarantined
- PS-ACE100-2005-10038 recommends the wedge test
- Path to durable bonds is there but obscure
- FAR 2x.603 should mandate bond **durability** testing




Injection repairs

- “Repairs” macro-voids detected by post-production NDI
 - Injected paste adhesive fills the void
 - NDI can no longer detect void
- Strength not restored in any way
 - Adhesive bonds rely on chemical reactions
 - Surface of void is fully reacted out during cure cycle
 - Not sufficiently energetic to enable a bond to occur
- *Same applies for repair of production voids in laminated composites*
- SHOW ME THE MONEY!!!
 - Is there ANY evidence to demonstrate ANY strength restoration?
 - Yet these are considered approved “terminating” repairs
- Should be limited to production macro-voids smaller than DTA limits




Case study: rudder production defect

- Rudder failed at high loads
- Fatigue cracking in skin adjacent to mast
- Large area of injection “repair” between core and mast



Case study: rudder production defect

- Injection easily separated from original adhesive
 - Was never bonded
 - Repair was totally ineffective
- Shear loads from core had to be transferred by the skins
 - Led to fatigue cracking of skin
- Crack was critical at high loads, failure occurred
- Injection repair was *never* effective and exceeded DTA limits
- Injection must be banned*



Nirvana

- *If and only if:*
 - Adhesion/mixed mode failure is prevented by using hydration resistant processes
 - Design methodology is based on excluding bond failure
 - Micro-voiding is avoided by environmental controls, and
 - Injection repairs limited to non-significant production defects
- THEN bonds should NEVER fail
- NDI and DTA only for accidental damage, not repetitive inspection for disbonding
- How much would the cost of maintenance be reduced?
- How much would flight safety improve?



Conclusions

- DTA and NDI are effective for production macro-voids
- DTA and NDI are **NOT** effective for production micro-voids or service disbonds
- Failure forensics must be the first step in assessing bond failures, or attempts to use DTA for anything other than macro-void cohesion failures may be a risk to flight safety
- Injection repairs must be banned except for production macro-voids within DTA limits



Question time

