



The relevance of Additive Manufacturing anomalies dimensions, amounts and locations.

Armando Coro

Nov 2021. WG2 Breakout sessions: F&DT and NDI of AM. (EASA-FAA Industry-Regulator AM Event.)

PROPIETARY INFORMATION - CONFIDENTIAL

© Industria de Turbo Propulsores S.A.U. and/or its subsidiaries – 2018

The information in this document is the property of Industria de Turbo Propulsores S.A.U and/or its subsidiaries and may not be copied or communicated to a third party, or used for any purpose other than that for which it is supplied without the express written consent of Industria de Turbo Propulsores S.A.U and/or its subsidiaries.



A Rolls-Royce
company


Index

The relevance of Additive Manufacturing anomalies dimensions, amounts and locations.

AM anomaly location relevance	3
Internal, superficial and sub-superficial anomalies	
AM anomaly size parameters relevance	4
Size and surface distance	
AM anomaly size parameters management	5
Dimensions correlation and principal component analysis	
AM anomaly size and amount impact	7
Example: Replacement of Welded Components by Additive Manufacturing...	
AM anomaly assessment “calibration”,...	8
Example: Inspection scheduling based on reliability updating. Defect size...	

AM anomaly location relevance

Internal, superficial, and sub-superficial defects



$$\Delta K = \frac{\lambda_w}{\Theta} \cdot (\lambda_t \cdot \sigma a + \lambda_b \cdot \sigma b) \cdot \sqrt{\pi \cdot a}$$

Newman, Raju & Picard.

$\sqrt{\text{Area}}$ 1.0

Stress Int. ΔK 1.12



$$\Delta K_w = \left(\frac{4}{5} + \frac{1}{5} \cdot \left(\frac{t_w}{t_w - 2a} \right) \right) \left(1 - \frac{0.23}{2b/2a} \right) \left(\frac{13}{15} + \frac{2}{15} \cdot \left(1 + \frac{a}{d} \right) \right) \cdot (\sigma a_w) \cdot \sqrt{\pi \cdot a}$$

Tada et al. & Coro et al., Sub-superficial

0.5

1.12 - 0.45




$$\Delta K_w = \left(\frac{2}{\pi} \cdot \sigma a_w \right) \cdot \sqrt{\pi \cdot a}$$

Tada et al.

$\sqrt{\text{Area}}$ 0.5

Stress Int. ΔK 0.45





The defect area and the stress intensity factor approaches gives a similar defect size relevance.
But, does it not work for the sub-superficial defects?

3

Anomaly size parameters relevance

Anomaly size and anomaly surface distance



The “a” defect dimension is the most relevant defect parameter

In addition, the sub-superficial defects behavior depend of the distance to the surface. The “d” distance need to be considered in the defect relevance evaluation.


Anomaly size parameters management

Anomalies dimensions correlation and principal component analysis


3 steps to evaluate a multi-parameter defect a,b,d:

1. Correlation matrix [C].
2. The use of the multivariable normal distribution (log-normal).
3. Principal component analysis.

$$1 \quad c_{i,j} = \sum_{k=1}^n ((v_i)_k \cdot (v_i)_k)$$



$$f(v_1, \dots, v_N) = \frac{1}{(2\pi)^{\frac{N}{2}} \cdot \sqrt{|C|}} \cdot e^{\left(-\frac{1}{2} \cdot (v_1, \dots, v_N)^T \cdot [C]^{-1} \cdot (v_1, \dots, v_N) \right)}$$




$$3 \quad \begin{bmatrix} (\sigma_{vp_1})^2 & 0 & 0 \\ 0 & \dots & 0 \\ 0 & 0 & (\sigma_{vp_n})^2 \end{bmatrix} = [Vp_1 \quad \dots \quad Vp_n] \cdot [C] \cdot [Vp_1 \quad \dots \quad Vp_n]^T$$

* Coro, A.(2021). PhD thesis. Planning the maintenance of gas turbine welded structures, by continuously updating of the reliability calculation. Department of Mechanical Engineering – Faculty of Engineering Bilbao. (TESEO Database).

Example: anomaly size management



Anomalies dimensions correlation and principal component analysis example



* Coro, A.(2021). PhD thesis. Planning the maintenance of gas turbine welded structures, by continuously updating of the reliability calculation. Department of Mechanical Engineering – Faculty of Engineering Bilbao. (TESEO Database).

AM anomaly size and amount impact

Example: Replacement of Welded Components by Additive Manufacturing Spare Parts




* Coro, A., Macareno, L.M., Aguirrebeitia, J., y López de Lacalle, L.N. (2019). A Methodology to Evaluate the Reliability Impact of the Replacement of Welded Components by Additive Manufacturing Spare Parts. Metals, 9(9), 932.

AM anomaly assessment “calibration”,...

Example: Inspection scheduling based on reliability updating. An anomaly size/amount based update.

Component reliability can be improved based on component test, inspection,...

- 4 loops process have been developed.
 - Reliability evaluation.
 - Variable contribution.
 - Test and inspection prediction.
 - Mechanistic model and variables update.
- The process allows to continuously updating of the reliability calculation



* Coro, A., Abasolo, M., Aguirrebeitia, J., y López de Lacalle, L.N. (2019). Inspection scheduling based on reliability updating of gas turbine welded structures. *Adv. Mech. Eng.* 11, 1–20.

