



EASA
European Aviation Safety Agency

Metallic Material strength properties and design values

Aiko Dühne
aiko.duehne@easa.europa.eu
Structures Expert

Rotorcraft & VTOL Structures Workshop
19-20 February 2019





CS 23.613: Material strength properties and design values

- Material strength properties must be based on enough tests of material **meeting specifications** to establish **design values** on a **statistical basis**.
- The design values must be chosen to **minimise** the probability of **structural failure** due to **material variability**
- The **design** of structure must **minimise** the probability of **catastrophic fatigue failure**
- **Thermal effects** must be considered where **significant**




Values to be used

- Compliance must be shown by selecting design values that assure material strength with the following probability:
- **“A-values”**: Single load path (lugs):
At least **99 percent** of the population of values are expected to equal or exceed the A-Value, with a confidence of **95 percent**.
- **“B-values”**: Multiple load path (skin-stringer-comb.):
At least **90 percent** of the population of values are expected to equal or exceed the B-Value mechanical property allowable with a confidence of **95 percent**.



Values to be used





Values to be used

➤ S-Values

- The S-value is based on the minimum property value
- Statistical assurance associated with S-Basis values are only established since 1975 within limitations
- Within these limitations values since 1975 can be considered as estimated A-values
- The use of S-Value should be done **carefully** and needs to be **agreed with EASA**



Premium Selection

- Premium selection allows using design values greater than the guaranteed minimum
- A specimen of **each individual** item to be installed on the aircraft has to be tested to determine the **actual strength properties**
- Part has to have areas to obtain test specimen without destroying the part
- **Test procedures** and **acceptance** criteria must be specified on the design drawing



Typical Sources (Examples)

➤ **MMPDS**

Metallic Materials Properties Development and Standardization

➤ **ESDU 00932**

Metallic Materials Data Handbook

➤ **Handbuch Strukturberechnung (HSB)**

(Fundamentals and Methods for Aeronautical Design and Analyses)

The use handbook is restricted to the members of the industry working group IASB.



Fatigue data

- Fatigue data plotted in e.g. MMPDS may not apply directly to the design of structures
 - Fatigue curves are mean curves, **not** A- or B-basis
 - Fatigue data is based on smooth specimen
 - Fatigue data may not take into account specific stress concentrations unique to any given structural design.
 - Localized high stresses may be induced during the fabrication
 - All fatigue data require modification into allowables for design use.



EASA
European Aviation Safety Agency

Thank you for your attention!

Any questions....?

Your safety is our mission.

An agency of the European Union

